

DURASOL GP-ASB

The ultimate traditional bio-stable Milky, based on chlorine free technology offering significant improvements on tool life and surface finish against traditional milky products

FEATURES & BENEFITS

- ✓ Suitable for Sensitive alloys
- ✓ Superb surface finish
- ✓ Low top up rate
- ✓ Significant cost reduction
- ✓ Operator friendly
- ✓ Environmentally respectable
- ✓ Developed specifically for Aluminium
- ✓ Inhibited against staining of yellow metals



CREATED TO TAKE ON THE DIFFICULT

Suitable for use in both moderately soft and hard water and for the use on a wide range of difficult materials. The product is truly a 'multi-metal' fluid and is the perfect choice for all modern manufacturing, including automotive, aerospace and high end manufactured components.

DESIGNED TO GIVE OUTSTANDING PERFORMANCE

Durasol GP ASB offers excellent cutting performance and can be used in all types of arduous manufacturing applications. The performance additives incorporated into the fluid provide outstanding surface finish on all types of aluminium and yellow metals. The unique formulation prevents scum and soap formation associated with more reactive materials.

Durasol GP ASB is an outstanding General Purpose fluid, capable of being used in stand alone machines or centralised systems

MULTI PURPOSE AS STANDARD

Durasol GP ASB has been developed to exhibit full multi-metal compatibility and is suitable for use on critical aerospace materials and alloys that are used in today's aircraft industry. To be used in both soft and hard water conditions from 100ppm – 350ppm

MATERIALS & PERFORMANCE

Material types	Performance rating	Applications	Dilution
Titanium	***	Tapping	8-10%
Aluminium	****	Milling	5-7%
Aero aluminium alloys	****	Turning	5-7%
High alloy/stainless steel	****	Reaming	8-10%
Copper/brass	***	Sawing	5-7%
Cast iron	***	Drilling	8-10%
Ferrous Materials	****	Grinding	4-6%

TYPICAL PHYSICAL PROPERTIES

Appearance	Amber liquid
Emulsion Type	Milky white
Foaming Tendency @ 5% emulsion in 50ppm water	Nil foam after 5 seconds
Specific Gravity at 20°C	0.976 typical
pH @ 5%	9.3 typical
Refractometer Factor	1.0
IP 287 Corrosion Break Point, % Volume:	2.0
Reichert Lubricity Characteristics at 10% dilution;	
Noise Reduction (metres)	39
Load Bearing Capacity (Kg/mm ²)	1.55

PRODUCT MANAGEMENT

Teklube advise the use of automated mixing systems. If mixing manually, always add the concentrate to the water with maximum agitation, if water is added to the concentrate, the emulsions may prove unstable. Avoid mixing with very cold concentrate or water. Check emulsion strength using a calibrated refractometer. Details of where to purchase equipment and how to use it are available from the Teklube Technical Department.

PRODUCT MANAGEMENT

The working concentration should be carefully controlled and monitored on a daily basis as higher and lower working concentrations have health and safety implications. Machines should be cleaned out regularly. Fluid and particulate contaminants should be kept to a minimum. This is important especially in terms of bacterial control and is in line with the latest advice from government and professional sources. Detailed reference sources are quoted in the

STORAGE

- ✓ Store in a cool, well ventilated area
- ✓ Store inside, between 10°C and 30°C
- ✓ Store away from direct heat and frost
- ✓ Avoid water collecting on the barrel top
- ✓ Shelf life 12 months from the date of manufacture